

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (original): An aqueous water- and oil-repellent dispersion comprising:

- (I) a homopolymer or copolymer comprising at least one polymerizable compound having a perfluoroalkyl or perfluoroalkenyl group and an acrylate, methacrylate or alpha-substituted acrylate group, or

a copolymer comprising said polymerizable compound and another compound copolymerizable therewith, and
- (II) a surfactant comprising:
 - (a) a nonionic surfactant having an HLB of less than 12, (b) a nonionic surfactant having an HLB of not less than 12 and less than 17, and (c) a nonionic surfactant having an HLB of not less than 17.

2. (original): The aqueous water- and oil-repellent dispersion according to claim 1, wherein the nonionic surfactants (a), (b) and (c) are present at an emulsion polymerization.

3. (currently amended): The aqueous water- and oil-repellent dispersion according to claim 1 or 2, which comprises at most 15 parts by weight, based on 100 parts by weight of total of the

nonionic surfactants, of a cationic surfactant, an anionic surfactant or an amphoteric surfactant as another surfactant.

4. (currently amended): The aqueous water- and oil-repellent dispersion according to claim 1-~~or~~ 2, which does not contain another surfactant and contains only the nonionic surfactants (a), (b) and (c).

5. (currently amended): The aqueous water- and oil-repellent dispersion according to claim 1~~anyone of claims 1 to 4~~, wherein the amount of the nonionic surfactant (b) is at least 50% by weight, based on total of the nonionic surfactants (a), (b) and (c).

6. (original): The aqueous water- and oil-repellent dispersion according to claim 1, wherein the weight ratio of the nonionic surfactant (a):the nonionic surfactant (b):the nonionic surfactant (c) is 10 to 40:50 to 80:5 to 30.

7. (currently amended): A textile to which the aqueous dispersion according to claim 1~~anyone of claim 1 to 6~~ is applied.

8. (currently amended): A method of processing a textile, which comprises using the aqueous dispersion according to claim 1~~anyone of claim 1 to 6~~.